See https://pubs.acs.org/sharingguidelines for options on how to legitimately share published articles.

In this paper, we demonstrate a system in which we use a topological line defect in the LC that traps QDs and well-defined gold nanorods (GNRs) along two dimensions but allows for controlled movement along one dimension (along the defect line) (Figure 1). The GNRs can be moved along the defect line by using infrared laser tweezers and can be manipulated to form a linear "sandwich" structure, where the QD is localized between the tips of two nanorods, so that it resides in a well-defined optical field geometry. In this way, we can study the emission behavior of a single dot, as well as how the emission is influenced when the QD is sandwiched between GNRs inducing a well-defined plasmon-enhanced electromagnetic field. We show that the plasmon coupling induces multiphoton emission and discuss how our findings may have an impact on the ability to design and realize mesostructured composite materials with unique physical behavior arising from controlled plasmon−exciton interactions.

RESULTS AND DISCUSSION

Elastic Trapping of Nanoparticles in a LC Line Defect. We used 40 × 65 nm GNRs (Figure 1), which were synthesized by following the seed-mediated method described in detail elsewhere[25−27] (see Materials and Methods). We also utilized commercially available CdSe/ZnS core−shell QDs (Ocean Nanotech) shown in Figure 1e, which were selected for their emission peak at 620 nm. These QDs are characterized by an average diameter of 10 nm with a CdSe core and a thin outer shell of ZnS forming a core−shell-type structure. The design of our experiments was aimed to control the optical coupling between QDs and GNRs. For this reason, we chose to use GNRs that exhibit a longitudinal surface plasmon resonance (SPR) peak at about 620 nm, matching the emission peak of QD particles (as measured when deposited on a glass substrate). The 10 nm silica shells of GNRs effectively make their SPR properties insensitive to the LC electric and order parameter tensor structures around nanoparticles within the surrounding host medium. As designed, our estimates show that, because of the shells, variations of the director structure within the LC do not cause shifts of SPR peaks for more than 3 nm. The core−shell QD particles also provide a high quantum

the sample and W_c is energy per unit length of the isotropic disclination core.[31] By following ref [31], one can calculate the reduction in defect energy that enables the trapping of nanoparticles as $\approx 23 k_B T$ for QDs and $\approx 450 k_B T$ for GNRs. Owing to the smaller polarizable volume of the QDs, laser tweezers at moderate powers of up to 50 mW for the polarizability of nanoparticles do not exert optical trapping

0.25, indicating single photon emission, with an exciton lifetime
= 14.2 ns, which is close to the value previously reported for
CdSe QDs with core–shell structure[53]. Following this

of the emission light due to the antenna-like arrangement, increased "on" [54]. Furthermore, we have performed a detailed analysis of the blinking trajectories by constant thresholding method and calculated the probability distribution of "on" (t_{on}) and "off" (t_{off}) times of the fluorescence emission, as shown in Figure 5c,d. A power law dependence, typical of the QD emission with